



EUROPLEX®
Film

EUROPLEX® HC Film 99710

Product

EUROPLEX® Film HC 99710 is a weather resistant, transparent, co-extruded PMMA and PVDF film for high quality lamination systems.

This film displays excellent performance in long term outdoor weathering without showing any color change or yellowing.

EUROPLEX® HC Film 99710 provides high protection for other polymeric substrates against degradation caused by UV radiation.

Thanks to its PVDF top layer, the film displays a very good chemical resistance, anti-soiling and easy-to-clean effect.

Application

EUROPLEX® HC Film 99710 can be laminated as a protective top layer onto polymeric films and sheets based on PVC, ABS, PC and ASA.

Decorative films protected with this film on top can be laminated on different substrates, such as PVC profiles.

In labels and graphic arts, EUROPLEX® HC Film 99710 can be used as a clear overlay in laminate systems for high UV and weathering protection. This also ensures chemical resistance, anti-soiling and easy-to-clean effects are achieved.

Processing

EUROPLEX® HC Film 99710 is only suitable for back printing, on the PMMA side, by a wide variety of printing technologies.

EUROPLEX® HC Film 99710 can be laminated onto polymeric substrates such as films and extruded sheets based on PVC, PC, ABS, PMMA and ASA by in-line or roll-to-roll heat lamination.

High quality laminates can also be achieved using EUROPLEX® HC Film 99710 and other polymeric substrates such as PET, PC, PP, PE and PVC, with the help of pressure sensitive adhesives (PSA) or solvent based adhesives.

The film can be cut-to-size or die cut.

Sales range

EUROPLEX® HC Film 99710 is delivered in standard rolls of 53 µm thickness, 48 µm PMMA layer and 5 µm PVDF top layer and 1450 mm width.

Custom-made rolls (up to 2700 mm in width) can be produced under prior commercial agreement.



Technical data			
Properties	Test method	Unit	Value
Optical			
Luminous transmittance (D65/10°)	DIN EN ISO 11664	%	93
UV transmittance (280 – 380 nm)	DIN EN 410:2011	%	≤ 1.5
Haze	ASTM D1003	%	5.3
Mechanical			
Tensile yield stress (σ_y)	DIN EN ISO 527-3	MPa	38
Yield strain (ϵ_y)	DIN EN ISO 527-3	%	6
Nominal strain at break (ϵ_{IB})	DIN EN ISO 527-3	%	≥ 50
Miscellaneous			
Accelerated weathering resistance	DIN EN ISO 4892-2, method A, cycle 1	h	10000 No visible change
Density	DIN EN ISO 1183	g/cm ³	1.2
Surface tension	DIN ISO 8296	mN/m	26

POLYVANTIS GmbH

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.polyvantis.com

® = registered trademark

EUROPLEX is a registered trademark of POLYVANTIS GmbH, Germany.

Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.