



Sheet material, aviation grade

EUROPLEX® F10 is based on a polycarbonate blend. The sheet meets the regulations for fire behavior of materials in the aircraft cabin including OSU heat release requirement. It is ideally suitable for vacuum deep-drawing and can be used to thermoform parts for aircraft seats, tables, trays, wall covers and other components in the cabin. EUROPLEX® F10 is made to customer needs in several colors and with a mat texture (hair cell) on one side.

Aviation requirements and approvals

| Requirement | |
|--|------|
| FAR 25.853 (a) (1) (i); AITM 2.0002; 60 s vertical burn | pass |
| FAR 25.853 (a) (1) (ii); AITM 2.0002; 12 s vertical burn | pass |
| FAR 25.853 (c); AITM 2.0006; (OSU) Heat release 65/65 | pass |
| FAR 25.853 (c); AITM 2.0007; Smoke density | pass |
| AITM 3.0005; Toxicity | pass |

Physical properties

| Property | Test method | Unit | Typical value |
|--|---------------|-------------------|---------------|
| Density | ISO 1183 | g/cm ³ | 1.30 |
| Tensile modulus | ISO 527 | MPa | 3100 |
| Tensile stress at yield | ISO 527 | MPa | 45 |
| Tensile strain at break | ISO 527 | % | 12 |
| Vicat softening temperature | ISO 306 | °C | 130 |
| Charpy impact strength | ISO 179-1/1fU | kJ/m ² | No break |
| Charpy notched impact strength | ISO 179-1/1eA | kJ/m ² | 15 |
| Burning behavior UL 94V (own test), 1.5 mm | UL 94V | class | V0 |

Sales range

| Property | Dimension [mm] |
|------------------|----------------|
| Extrusion width | 1250 or 1400 |
| Extrusion length | Up to 3000 |
| Thickness | 1.0 – 4.0 |



Röhm GmbH
Acrylic Products

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.roehm.com

® = registered trademark

EUROPLEX is a registered trademark in EU and a filed trademark in US of Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.