



Product

The electrostatic dissipative polycarbonate sheet provides a permanent protection against electrostatic discharge events (ESD).

EUROPLEX® SDX Glazings dissipate electric charges in a controlled way against earth. EUROPLEX® SDX-F is suitable for heat-bending.

Product properties*	Value	Unit	Test method
Electrical			
Surface resistivity	10 ⁵⁻⁷	Ohm/sq	DIN IEC 60093
Physical			
Density	1,20	g/cm ³	ISO 1183-1
Optical			
Light transmission factor	85	%	DIN 5033, DIN 5036
Light reflection factor	7	%	DIN 5033, DIN 5036
Haze	3,5	%	ASTM D 1003
Mechanical			
Tensile strength	60	MPa	ISO 527
Modulus of elasticity	2400	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Extensibility	6	%	ISO 527
Nominal elongation	70	%	ISO 527
Bending modulus	2100	MPa	ISO 178
Bending strenght	100	MPa	ISO 178
Bending stress at rupture	no rupture		ISO 178
Bending stress at 3.5 %	80	MPa	ISO 178
Edge fibre elongation at rupture	no rupture		ISO 178
Edge fibre elongation at bending strength	6	%	ISO 178
Compression modulus of elasticity	2400	MPa	ISO 604
Compression strength	70	MPa	ISO 604

Product properties*	Value	Unit	Test method
Mechanical			
Nominal compression at compression strength	8	%	ISO 604
Compression yield stress	70	MPa	ISO 604
Charpy impact strength	no rupture		ISO 179
Charpy notched bar impact strength	11	kJ/m ²	ISO 179
Thermal			
Vicat softening point	145	°C	ISO 306
Thermal expansion coefficient	7 x 10 ⁻⁵	1/K	ASTM D 696

* All data are related to sheets with 3 mm thickness.

Röhm GmbH
Acrylic Products

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.roehm.com

® = registered trademark

PLEXIGLAS and EUROPLEX are registered trademarks of Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.