



## PLEXIGLAS® Optical OZ024

### Product

PLEXIGLAS® Optical OZ024 meets extremely high optical requirements. Its high light transmission – especially over long light paths – makes it the ideal acrylic for light guides and edge lighting.

PLEXIGLAS® Optical OZ024 is a clear, highly transparent solid sheet made of extruded acrylic (polymethyl methacrylate, PMMA). With the appropriate printing, laser-cutting or routing, PLEXIGLAS® Optical ensures that the input light is emitted towards the viewer with almost no losses. Compared with conventional acrylic, PLEXIGLAS® Optical OZ024 makes it possible to produce energy-saving installations with the same luminance.

### Properties

In addition to the well-known, tried and tested properties of PLEXIGLAS®, such as

- excellent light transmission and brilliance
- very high weather resistance
- ease of fabrication
- high surface hardness
- light weight – half the weight of glass
- 11 times the impact strength of glass
- 100% recyclability,

PLEXIGLAS® Optical OZ024 offers the following special features:

- high luminous efficiency even if large areas are to be illuminated: transmission is  $\geq 91\%$  at lengths of 150mm, which is 5% higher than for typical extruded acrylic
- extremely high purity and clarity
- absolute colorlessness

### Applications

Owing to these properties, PLEXIGLAS® Optical OZ024 is particularly suitable for manufacturing large or medium-sized edge-lit light guide panels

- for illuminated signs
- and for display applications.

### Fabrication

PLEXIGLAS® Optical OZ024 can be fabricated just like standard PLEXIGLAS®. The following Guidelines for Workshop Practice are available for working with PLEXIGLAS®:

- Machining PLEXIGLAS® (No. 311-1)
- Forming PLEXIGLAS® (No. 311-2)
- Joining PLEXIGLAS® (No. 311-3)
- Surface Treatment of PLEXIGLAS® (No. 311-4)
- Fabricating Tips for PLEXIGLAS® Solid Sheets (No. 311-5)

### Product range

The product is only available on request  
[info@plexiglas.de](mailto:info@plexiglas.de)

Properties/Typical Values			
	PLEXIGLAS® Optical OZ024	Unit	Test standard
<b>Mechanical properties</b>			
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Charpy impact strength	15	kJ/m <sup>2</sup>	ISO 179/1fu
<b>Thermal properties</b>			
Vicat softening temperature	104	°C	ISO 306
<b>Optical properties</b>			
Transmittance 3 mm thickness	92	%	DIN 5036-3
Transmittance 150 mm rod	91	%	Manufacturer process
Refractive index	1.49	-	ISO 489
Haze	< 1	%	ASTM D 1003
<b>Behavior towards water</b>			
Max. increase in weight after water storage	2.1	%	ISO 62, Method 1

For further typical values, please see Technical Information PLEXIGLAS® GS/XT (211-1).

**Röhm GmbH**  
Acrylic Products

Riedbahnstraße 70  
64331 Weiterstadt  
Germany

**www.plexiglas.de**  
**www.roehm.com**

® = registered trademark

PLEXIGLAS is a registered trademark of Röhm GmbH, Darmstadt, Germany.  
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.