


PLEXIGLAS®
Multi-skin sheet


PLEXIGLAS® Heatstop Cool Blue S5P 32/1230-32 WZ009



Product

PLEXIGLAS® Heatstop Cool Blue S5P 32 is an infrared (IR)-reflecting, highly heat-insulating and extremely weather-resistant quintuple-skin sheet made of impact-modified acrylic (polymethyl methacrylate, PMMA). The Heatstop coating is uniformly and permanently fused with the sheet material and is equally effective on the upper and lower side of the sheet.

Cross-section of PLEXIGLAS® Heatstop Cool Blue S5P 32 (dimension in mm)



Properties

Besides the general properties of PLEXIGLAS® like

- Excellent light transmission and brilliance
- Outstanding weather resistance
- 100% recycling ability
- Easy to fabricate
- High surface hardness

PLEXIGLAS® Heatstop Cool Blue S5P 32 possesses the following properties:

- Incident solar energy is reduced by as much as 78 %.
- The color impression beneath the glazing is very pleasant and cool.
- The sheets offer excellent protection against an excess of harmful UV radiation.
- They are impact-resistant during transport, handling and installation.
- They are highly heat-insulating.
- They help to save energy and minimize CO² emissions.
- They are hail-resistant (to hailstones with an impact energy up to 1 joule).
- This comes with a 10-year guarantee.

Applications

Due to these properties PLEXIGLAS® Heatstop Cool Blue S5P 32 is suitable for the following applications:

- Carports
- Conservatories
- Façades
- Greenhouses
- Patio roofs
- Porches
- Skylights
- Verandas
- etc.

Processing

For PLEXIGLAS® Heatstop Cool Blue S5P 32 the following processing guideline is available:

- Instructions for Installing PLEXIGLAS® Multi-Skin, Corrugated and Solid Sheets (Ref-No. 311-8)

Product range

PLEXIGLAS® Heatstop Cool Blue S5P 32 is available in the following grades and sizes:

- Length: 2000 bis 7000 mm
- Width: 1230 mm
- Colors: White (bluish-golden)

For details please refer to the PLEXIGLAS® sales handbook.

Heatstop Cool Blue Effect

The PLEXIGLAS® Heatstop Cool Blue multi-skin sheet very effectively reduces solar heat radiation by means of special technology. This effect is supported by its specific color, which also has a favorable influence on the perceived temperature, a factor that is very important for human wellbeing. The Heatstop Cool Blue coating gives the sheets an attractive golden surface gloss. Seen from below, the sheets have a cool, bluish look, as befits their function. This color has an iridescent effect. The color impression varies depending on the viewing angle and lighting conditions.

Heat insulation

With their further improved U-value, these sheets meet all requirements of the German Energy Saving Ordinance (EnEV). This makes them suitable as highly heat-insulating glazing materials for private construction as well as for factory units and sports halls.

NO DROP coating

The water-dispersing NO DROP¹ coating applied to one side of the sheet causes any surface water to flow off as a thin, continuous film. When the sheet is installed with the NO DROP coating on the outside of the roof, it supports natural cleaning by rainwater. Installed on the inside of the roof, the coating helps to prevent dripping from condensation and the damage this may cause. The NO DROP coating is covered with a protective layer applied during the manufacturing process. This protective layer can be washed off with water and a sponge, or by hosing down the sheet. This activates the NO DROP coating.

Load-bearing capacity Support spacing

Thanks to their high rigidity, these sheets allow large spans, which reduce shadows inside the room and cuts construction costs. Supported on all four sides, the PLEXIGLAS® Heatstop Cool Blue S5P 32/1230 quintuple skin sheet requires no additional cross-members at a load of up to 1,000 N/m². The spacing stated in the table applies to greater loads. The loadbearing capacity of PLEXIGLAS® Heatstop Cool Blue S5P 32/1230 is determined in line with ETAG 010 (Guideline for European Technical Approval for Self-supporting, Translucent Roof Kits), assuming a rebate depth of 20 mm for the multiskin sheets in the glazing system. The support spacing should be reduced correspondingly for smaller rebate depths.

¹ Europ. Patent 149 182

Support spacing

Load [N/m ²]	Support spacing [m]
750	no cross members
1000	no cross members
1250	5,7
1500	4,2
1750	3,7
2000	3,3
2250	3,1
2500	2,9
2750	2,7
3000	2,6

Brandverhalten

- Im Brandverhalten ist PLEXIGLAS® in die europäische Klasse E nach DIN EN 13501 eingestuft.
- PLEXIGLAS® brennt nahezu rauchfrei nach DIN 4102 und ist leicht zu löschen.
- Die Rauchgase von PLEXIGLAS® sind nicht akut giftig nach DIN 53436 und nicht korrosiv nach DIN VDE 0482-267.
- Lichtflächen aus PLEXIGLAS® im Dach können im Brandfall aufschmelzen und als Rauch- und Wärmeabzug wirken.

Technical data (Typical values)	
Available length	2000 to 7000 mm
Light transmittance τ_{D65}	
White WZ009	18%
Total energy transmittance g	
White WZ009	15%
Heat transfer coefficient k	1,5 W/m ² K
Coefficient of linear thermal expansion α	0,09 mm/m ² K
Possible expansion due to heat and moisture	approx. 6 mm/m
Max. service temperature without load	70 °C
Weighted sound reduction index	24 dB
Area weight	approx. 5,8 kg/m ²

Garantie

Garantiebedingungen zu diesem und weiteren Produkten finden Sie unter www.plexiglas.de.

Röhm GmbH
Acrylic Products

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.roehm.com

® = registered trademark
PLEXIGLAS is a registered trademark of Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.