



PLEXIGLAS®
Film

PLEXIGLAS® Film OF096

Product

PLEXIGLAS® Film OF096 is a high weather resistant, glossy, and transparent acrylic film for graphic printings and high quality laminations.

Due to its excellent performance under weathering and UV light exposure, PLEXIGLAS® Film OF096 does not present color change or yellowing. Therefore it provides high protection of laminating systems from degradation caused by UV radiation.

Its glossy and smooth surface leads the film to have a high optical quality surface.

Application

PLEXIGLAS® Film OF096 can be easily printed on as film decoration and then laminated on different polymeric films and sheets. Laminated decoration films based on PLEXIGLAS® are suitable for a wide range of molding processes such as thermoforming and insert molding.

In labels and tapes, PLEXIGLAS® Film OF096 can be used as single face layer or clear overlay in laminated film systems for UV and weathering protection. High gloss and quality finishing are achieved.

Thanks to its good optical properties and lamination with pressure sensitive adhesives (PSA), PLEXIGLAS® Film OF096 is highly recommended for traffic control signs.

PLEXIGLAS® Film OF096 has good optical properties which allows the film to be used as overlay in ID cards.

Processing

PLEXIGLAS® Film OF096 has excellent printability and can be easily printed on using all technologies such as gravure, flexography and digital. In most cases any pre-treatment or primers are not required.

PLEXIGLAS® Film OF096 can be laminated onto polymeric substrates such as films or extruded sheets based on PVC, PC, ABS, PMMA and ASA by in-line or roll-to-roll heat lamination.

Laminates can also be achieved using PLEXIGLAS® Film OF096 and other polymeric substrates such as PET, PC, PP, PE and PVC, with the help of PSA or solvent based adhesives.

The film can be cut-to-size or die cut.

Sales range

PLEXIGLAS® Film OF096 is delivered in standard rolls of 75 µm thickness, 1270 mm width, and 1000 m length.

Custom-made rolls (up to 2800 mm in width) can be produced under prior commercial agreement.



Technical data			
Properties	Test method	Unit	Value
Thickness		µm	75
Optical			
Luminous transmittance (D65/10°)	DIN EN ISO 11664	%	92
UV transmittance (280–380 nm)	DIN EN 410	%	< 1
Yellowness index (D65/10°)	ISO 17223		< 1
Haze	ASTM D1003	%	4.5
Mechanical			
Tensile yield stress (σ_y)	DIN EN ISO 527-3	MPa	31
Yield strain (ϵ_y)	DIN EN ISO 527-3	%	7
Nominal tensile strain at break (ϵ_{tB})	DIN EN ISO 527-3	%	> 50
Thermal			
Glass transition temperature T _g (DSC)	DIN EN ISO 11357	°C	106
Miscellaneous			
Accelerated weathering resistance	DIN EN ISO 4892-2, method A, cycle 1	h	8000 No visible changes
Density	DIN EN ISO 1183	g/cm ³	1.13
Surface tension	DIN EN ISO 8296	mN/m	38–42

POLYVANTIS GmbH

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.polyvantis.com

® = registered trademark

Semi-finished polymethyl methacrylate (PMMA) products from POLYVANTIS are sold on the European, Asian, African and Australian continents under the registered trademark PLEXIGLAS®, in the Americas under the registered trademark ACRYLITE®, both owned by Röhm GmbH, Darmstadt, or its affiliates. Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.