

Technical Information**PLEXIGLAS® FILM 0F086T****PRODUCT DATA SHEET****PRODUCT**

PLEXIGLAS® Film 0F086T is a clear acrylic film for outdoor applications with one side structured surface.

Due to its excellent performance under long-term weathering and UV light exposure, PLEXIGLAS® Film 0F086T does not present color change or yellowing.

Therefore, it provides an enhanced protection of plastic substrates from degradation caused by UV wavelengths.

APPLICATION

PLEXIGLAS® Film 0F086T is suitable as top layer for high UV and weathering protection of fiber reinforced polyester sheets.

Due to its one side structured surface PLEXIGLAS® 0F086T scatters the light but still has a very good light transmission.

PROCESSING

PLEXIGLAS® Film 0F086T shows very good adhesion to fiber-reinforced polyesters.

The film can be directly coated on liquid styrene/MMA resin before curing..

SALES RANGE

PLEXIGLAS® Film 0F086T is delivered in standard rolls of 150µm thickness and 1080mm width.

Tailor made rolls can be produced, under prior commercial agreement.

TECHNICAL DATA

Properties	Test method	Unit	Value
Optical			
Luminous transmission (D65)		%	88
L* (in transmission, D65)			95.2
a* (in transmission, D65)			-0.26
b* (in transmission, D65)	DIN 5033 (8°/di), ISO 17223, ISO 11664		1.1
Color coordinates x (in transmission, D65)			0.315
Color coordinates y (in transmission, D65)			0.333
Yellowness Index			< 2.0
UV transmittance (280 – 380 nm)	ISO 489	%	< 0.1
Miscellaneous			
Accelerated weathering resistance	ISO 4892-2 method A, cycle 1	h	10000, No visible change

° = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

Evonik Industries is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK PERFORMANCE MATERIALS GMBH
Acrylic Products
Riedbahnstr. 70
64331 Weiterstadt
Germany

films@evonik.com
www.plexiglas.net
www.evonik.com

Ref. Nr. 239-70